



[Material Data Sheet]

## **304L** Stainless Steel



COMPOSITION %	
Fe	Balance
Cr	17.5 - 19.5
Ni	8 - 12
Mn	2 (max)
Si	1 (max)
P	0.045 (max)
S	0.03 (max)
N	0.1 (max)
C	0.03 (max)



MECHANICAL PROPERTIES 1		
	Shop System™	
	Standard	As-Sintered <sup>2</sup>
Ultimate tensile strength - xy (MPa)	ASTM E8M	577 ± 8
Yield strength - xy (MPa)	ASTM E8M	182 ± 4
Elongation - xy (%)	ASTM E8M	79 ± 5
Young's modulus - xy (GPa)	ASTM E111	188 ± 15
Notched Charpy impact energy - xy (J)	ASTM E23	75 ± 8.5
Hardness (HRB)	ASTM E18	68 ± 2
Density (g/cc)	ASTM B311	7.7 ± 0.06
PERFORMANCE <sup>3</sup>		
Boil test (corrosion)	ASTM F1089	Pass
Copper sulfate test (corrosion)	ASTM F1089	Pass

ATTRIBUTES & APPLICATIONS	
Structural components (e.g. housings & frames)	
Jewelry & decorative items	
Fluid transfer components (e.g. manifolds)	
Food processing equipment	
Welded components & assemblies	
OTHER STANDARD DESIGNATIONS <sup>4</sup>	_
UNS \$30403	
EN 1.4307	
X2CrNi18-9	

 $End-use\ material\ performance\ is\ impacted\ (+/-)\ by\ certain\ factors\ including\ but\ not\ limited\ to\ part\ geometry\ and\ design,\ application\ and\ evaluation\ conditions,\ etc.$ 

<sup>1.</sup> Mechanical properties noted represent mean values +/- 1 standard deviation across Xy & Yx orientations for as-printed samples.

<sup>2.</sup> Sintered in an Ipsen Titan H2 graphite hot zone furnace.

Prior to corrosion resistance testing, all test samples were passivated in accordance with ASTM A967.

<sup>4.</sup> Listed designations are for reference purposes only. Composition and mechanical properties may vary.